

Fair-Rite P/N 2743007112

43 Material Grade

Nominal Chemical Composition

<u>Compound</u>	<u>CAS Number</u>	<u>wt %</u>	Wt of core (g)= 0.4190	Compound Weight (g) Breakdown of 43 Material
Fe2O3	1309-37-1	65	0.27235	
ZnO	1314-13-2	21	0.08799	
NiO	1313-99-1	10	0.04190	
CuO	1317-38-0	4	0.01676	

Pb- Free Plated Round Cu Wire

<u>Element</u>	<u>CAS Number</u>	<u>wt%</u>	Wt of wire (g)= 0.1810	Element Weight (g) Breakdown of Pb- Free Plated Round Cu Wire
Cu	7440-50-8	94.4	0.17086	
Plating:				
Ni	7440-02-0	0.9	0.00163	
Sn	7440-31-5	4.7	0.00851	

Calculated Maximum Levels of RoHS Restricted Substances Present in 43 Material Grade

<u>Impurity Substance</u>	<u>RoHS Threshold (ppm)</u>	<u>ppm</u>	Wt of core (g)= 0.419	RoHS Impurity Substance Weight (g) Breakdown of 43 Material
Hexavalent chromium (Cr+6)	1000	0.00	0	
Cadmium (Cd)	100	6.10	2.5559E-06	
Mercury (Hg)	1000	0.10	4.19E-08	
Lead (Pb)	1000	11.00	0.000004609	
Polybrominated biphenyl (PBB)	1000	0.00	0	
Polybrominated diphenyl (PBDE)	1000	0.00	0	
Bis(2-Ethylhexyl) phthalate (DEHP)	1000	0.00	0	
Benzyl butyl phthalate (BBP)	1000	0.00	0	
Dibutyl phthalate (DBP)	1000	0.00	0	
Diisobutyl phthalate (DIBP)	1000	0.00	0	

Supporting notes:

1. P/N 2743007112 consists of:
 - a core 43 Material Grade
 - b wire Pb- Free Plated Round Cu Wire
2. Moisture Sensitivity Level (MSL)= 1
3. Max Reflow Temp= 260 degC
4. Max Time at Max Reflow Temp= 40 sec
5. RoHS 6/6 Compliant Terminations/ Wire are backwards compatible with standard Soldering Processes
6. RoHS Conversion Date= 1/1/2005
RoHS Compliance Marking is
7. Contained on Shipping Labels