

# Fair-Rite P/N **2743008111**

## 43 Material Grade

## Nominal Chemical Composition

<u>Compound</u>	<u>CAS Number</u>	<u>wt %</u>	Wt of core (g)= <b>0.507</b>	Compound Weight (g) Breakdown of 43 Material
Fe2O3	1309-37-1	65	0.3296	
ZnO	1314-13-2	21	0.1065	
NiO	1313-99-1	10	0.0507	
CuO	1317-38-0	4	0.0203	

## Pb- Free Plated Round Cu Wire

<u>Element</u>	<u>CAS Number</u>	<u>wt%</u>	Wt of wire (g)= <b>0.193</b>	Element Weight (g) Breakdown of Pb- Free Plated Round Cu Wire
Cu	7440-50-8	94.4	0.18219	
Plating:				
Ni	7440-02-0	0.9	0.00174	
Sn	7440-31-5	4.7	0.00907	

## Calculated Maximum Levels of RoHS Restricted Substances Present in 43 Material Grade

<u>Impurity Substance</u>	<u>RoHS Threshold (ppm)</u>	<u>ppm</u>	Wt of core (g)= <b>0.507</b>	RoHS Impurity Substance Weight (g) Breakdown of 43 Material
Cr+6	1000	0.00	0	
Cd	100	<b>6.10</b>	3.0927E-06	
Hg	1000	<b>0.10</b>	5.07E-08	
Pb	1000	<b>11.00</b>	0.000005577	
PBB	1000	0.00	0	
PBDE	1000	0.00	0	

### Supporting notes:

1. P/N 2743008111 consists of:
  - a core 43 Material Grade
  - b wire Pb- Free Plated Round Cu Wire
2. Moisture Sensitivity Level (MSL)= 1
3. Max Reflow Temp= 260 degC
4. Max Time at Max Reflow Temp= 40 sec
5. RoHS 6/6 Compliant Terminations/ Wire are backwards compatible with standard Soldering Processes
6. RoHS Conversion Date= 1/1/2005  
RoHS Compliance Marking is
7. Contained on Shipping Labels